

PREMIUM TEAK OIL 6151

Description

Product Description	High-quality penetrating wood oil for the care and maintenance of tropical woods such as teak, bangkirai, massaranduba, ipé, mahogany. For terrace floors, planks, tables, chairs, deck structures in shipbuilding, etc. outdoors. Intensifies the colour of the wood. High level of penetration.
Raw Material Base / Binder Type / Active Agent	Alkyd resin
Application	Biocide-free outdoor wood protection.
Gloss Level	20

Technical Data

Technical Data	Product	
Material Safety Data Sheet	615100	
Density (20°C)	0.860	g/cm ³
Solids Content	27	± 1 w/w-%
Organic Solvent Content	72	± 1 w/w-%
VOC Content (EU)	628	g/L
Shelf Life at 20°C in Unopened Original Containers	max. 30 Months	
Theoretical Coverage	75 g/m ² → 13 m ² /kg	
The data apply for: PREMIUM TEAK OIL 6151. Values can vary depending on color or gloss level.		

Safety Data

Refer to the following safety data sheets as well as the instructions on the label	
Product	615100 - PREMIUM TEAK OIL 6151-20


Application advice

Untreated wood substrate












Product	Data Sheet	Applied Quantity / Layer Thickness
Impregnation:	PREMIUM TEAK OIL 6151	6151
	Coat surface completely 1-3 times at an interval of 15 minutes	1-3x 75 g/m ²

For further application proposals please ask our representative.


Preparation

	Substrate	Every substrate must be well-cleaned, dry and free from grease and oil.
	New, raw wood	Only treat raw, dry, clean, and sanded wood (grain 80). Do not use on already lacquered surfaces.
	Grayed, dirty substrates	Pretreat with AUSSENHOLZ-ENTGRAUER N1480 (outdoor wood cleaner) according to the instructions in the relevant technical datasheet.

Processing

	Preventative Measures	We recommend wearing personal protective clothing, even in cases where no local regulations are in force.
	Stir	Stir or shake product well before each use.
	Dilution	Ready for use. If required, with TERPENTINERSATZ 4214-98
	Brush	Yes, with a brush or applicator (art. no. N9016).
	Roller	Yes
	Trowel	No
	Intercoat Abrasion	Application of another coat: Sand first after a minimum of 8 hours drying time.
	Coating Recommendations	See application recommendations on page 2.
	Maintenance Instructions	Regular maintenance with PREMIUM TEAK OIL 6151 is recommended, depending upon the degree of weathering. Perform 1 to 4 times annually. Remove dirt first. Only treat dry and clean wood. Apply PREMIUM TEAK OIL 6151 with a clean cloth, 1 to 2 times at an interval of 15 minutes. Rub in completely, allow to penetrate briefly and then wipe off excess oil while still wet.
	Additional Remarks	When using on native coniferous woods like fir, spruce or larch, pretreatment with STABILO FFF clear is recommended, if not essential as protection against blue stain. (Only for outdoor use). Ensure adequate ventilation during processing and curing. Hazard warning: rags soaked with teak oil can spontaneously combust under certain conditions and must therefore be kept in a closed metal waste bin until disposal.
	Information	Please note that clear coatings do not protect wood against UV radiation. For further information regarding the treatment and use of hardwood floors, please refer to www.parkett-verband.ch .

Drying Time

	Drying Time	At 23°C and 65% rel. humidity		
		Dust dry after:	2	hours
		Touch dry after:		
		Sandable after:		
		Recoat after:	8	hours
	Fully dry after:	7	days	

Important Remarks

Specific Restrictions	Should not be allowed to enter soil or groundwater.
Storage Conditions	Store product tightly closed between +5 and +30° C.
Coating Removal	Wood sanding
Equipment Cleaning	Immediately after use with TERPENTINERSATZ 4214-98

This data sheet is for your reference and information only. The above data are correct to the best of our knowledge. We offer no guarantees for use and exclude any liability. This applies in particular to consequential damage. We are not liable for any advice given by our employees. Our employees give non-binding information only. Site supervision, compliance with handling regulations, and adherence to recognized engineering rules are the responsibility of the manufacturer, even if our employee was on site during handling. Modifications due to technical developments may be made. The latest version of this information is applicable. In special cases, please request separate technical specifications.