

# TECHNICAL DATASHEET

**Description** : **UV-SEALER STANDARD**

**Product Number** : **661-205-0000**

**Description** : Colourless acrylic UV-curable sealer for roller application in the coating process of resistance flooring or PDL board. The UV-sealer shows excellent adhesion, sanding and sealing properties.

## Characteristics

*Viscosity* : 87 sec. in DIN 6mm at 25°C

*Density* : 1.2 ± 0.1 kg/l

*Solid Content* : 98 - 99%

*VOC* : Max 3%

*Classification* : Complies with the Environmental Protection Act of 1990.

## Application

*Preparation* : Stir well and check before use.

*Hardener* : Not required

*Thinner* : Not required

*Viscosity* : As delivered

*Film Weight* : Apply 20 - 30 g/m<sup>2</sup>.

*Mode* : Apply in roller machine with a shore hardness of offset rollers of 40-50 (Isobutylene / Isoprene-Copolymer or EPDM-Prepolymer).

*Curing* : Semi-cure: 70 - 80 mJ/cm<sup>2</sup>  
Surface cure: 190 - 200 mJ/cm<sup>2</sup>

**Substrate** : The product is specially formulated as UV sealer to be applied on TEKNOS TREFFERT COATINGS UV Filler. The product provides excellent support to TEKNOS TREFFERT COATINGS 651-/652- UV Topcoat. Please consult our technical staff prior to other applications.

# TECHNICAL DATASHEET

**Description** : **UV-SEALER STANDARD**

**Product Number** : **661-205-0000**

## **Storage**

*Shelf Life* : 6 months

*Conditions* : Protect from sunlight and frost.  
To be stored at 5 - 35°C.

## **Delivery**

*Packaging* : Available in 20 kg pails.

*Delivery Time* : Please allow 6 working days of production and transportation.

*Quantity* : Except for trial, minimum quantity is 100kg per individual product.

**Cleaning** : Use solvent such as butyl acetate for cleaning.

**Precautions** : Refer to Safety Data Sheet.

**Health & Safety** : Refer to Safety Data Sheet.